



LP-300 Woven Minimum Average Roll Values

PROPERTY	TEST PROCEDURE	LP-300
Grab Tensile Strength (W/F) (lbs)	ASTM D-4632	300
Grab Elongation (%)	ASTM D-4632	15
Trapezoid Tear (lbs)	ASTM D-4533	115
Puncture (lbs)	ASTM D-4833	145
Mullen Burst (psi)	ASTM D-3786	600
Permittivity (sec ⁻¹)	ASTM D-4491	.02
Permeability (cm/sec)	ASTM D-4491	.005
A.O.S. (U.S. Sieve)	ASTM D-4751	30
UV Resistance @500 hrs (%)	ASTM D-4355	90
Water Flow (gpm/ft ²)	ASTM D-4491	NA
Open Area (%)	CW02215	NA

[*Back to Specifications*](#)